

Flexline 1.5mm

Flexline is a propylene/ethylene copolymer geomembrane produced from a resin formulation designed to provide a premium quality geomembrane, with excellent flexibility, improved elasticity and resistance to puncture. These properties assure maximum multi-axial elongation to accommodate differential settlement. Flexline is ideal for most geomembrane applications and major benefits to installation are provided by a lower coefficient of thermal expansion and a wide temperature-welding window.

<u>Tested Property.</u>	<u>Test Method.</u>	<u>Min. Value.</u>
Nominal Thickness (mm)	ASTM D5199	1.50
Thickness (mm) minimum.	ASTM D751	1.35
Density (g/cm ³)	ASTM D792/ 1505 A	0.88
Tensile properties (each direction)	ASTM D638 Type IV Speed 50 mm pm	
Strength at Break (N/mm)		26
Elongation at Break % G L 50mm		960
Tear Resistance (N)	ASTM D1004	90
Puncture Resistance (N)	ASTMD4833	200
<u>Reference Property.</u>	<u>Test Method.</u>	<u>Nominal Values.</u>
Thickness (mm)	ASTM D5199	1.5
Multi-axial Strain	ASTM D5617	>100
Carbon Black		
Content (%)	ASTM D1603	3.0
Dispersion	ASTM D5596	Note 1
Dimensional Stability (%)	ASTM D1204	±1.0%
Low Temperature	ASTM 746	<-40
Brittleness °C	Condition B	
Melt Flow Index	ASTM D1238	<1.0
g/10 minutes	Cond. 190/2.16	

Note 1. Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.

TRANSPORT INFORMATION

Roll width: 5.7m
Roll length: 130m
Roll weight: approx. 1,000kg